

PART 1- GENERAL

1.1 SUBMITTALS

- A. Closeout Submittals: Submit the following:
 - 1. Warranty: Warranty documents specified herein.

1.2 DELIVERY, STORAGE & HANDLING

- A. Store materials protected from exposure to harmful weather conditions and at a temperature above 45° Fahrenheit.

1.3 WARRANTY

- A. Project Warranty: Refer to Conditions of the Contract for Project warranty provisions.
- B. Manufacturer's Warranty: Submit, for the owner's acceptance, the manufacturer's standard warranty document executed by an authorized company official. The manufacturer's warranty is in addition to, and not a limitation of, other rights the Owner may have under provisions of the contract documents.
 - 1. Warranty Period: Ten years commencing on the date of acceptance of the project by the Owner or Notice of Completion which ever is earliest.
 - 2. Warranty Terms: Terms to include moisture related failures, including all finish floor materials and labor. Admixture warranty issued on completion of ASTM-D-5084 or ASTM-D-4263 test and results submitted to a Concure Systems Representative.

PART 2- PRODUCTS

2.1 CONCRETE WATERPROOFING ADMIXTURE

- A. Manufacturer: Concure Systems 1618 E. Briarwood Terrace, Phoenix, AZ 85048
Contact: Emil Pikula Cell – (480) 820-7171, Fax (480) 820-7787, E-mail: epikula@cox.net
- B. Admixture: Concure Systems Admixture
- C. Accessory Materials.
 - 1. Concure Systems Crack Fill Binder.

2.2 MIXING

- A. Add 14 ounces of Concure admixture per 100 lbs. of cementitious material to ready mix truck at the batch plant, or jobsite before discharge, mix rapidly for 7 minutes. (Follow Manufacturer's Instructions).
- B. To be used in lieu of, designed, mix water. Not in addition to mix water. Do not alter water/cement ratio. w/c .45 or less and a maximum slump of 4 inches.

- C. The addition of non-chlorinated admixtures is permitted. (Follow Manufacturer's Instructions).

2.3 TESTING

- A. Concure recommends either ASTM D-5084 or ASTM 4263 only.
- B. Concure Systems must be provided test results if ASTM-D-5084 is performed and a Concure Systems Representative or designated agent must be present for final inspection of ASTM-D-4263 test.

2.4 PRODUCT SUBSTITUTIONS

- A. Substitutions allowed meeting the following criteria:

Product must have MINIMUM 10 years no fail experience in the flooring/Concrete industry.

See sections 7100, 9600, 9900

PART 1- GENERAL

1.1 SUBMITTALS

- A. Closeout Submittals: Submit the following:
 - 1. Warranty: Warranty documents specified herein.

1.2 DELIVERY, STORAGE & HANDLING

- A. Store materials protected from exposure to harmful weather conditions and at a temperature above 45° Fahrenheit.

1.3 WARRANTY

- A. Project Warranty: Refer to Conditions of the Contract for Project warranty provisions.
- B. Manufacturer's Warranty: Submit, for the owner's acceptance, the manufacturer's standard warranty document executed by an authorized company official. The manufacturer's warranty is in addition to, and not a limitation of, other rights the Owner may have under provisions of the contract documents.
 - 1. Warranty Period: Ten years commencing on the date of acceptance of the project by the Owner or Notice of Completion whichever is earliest.
 - 2. Warranty Terms: Terms to include moisture related failures, including all finish floor materials and labor. Admixture warranty issued on completion of ASTM-D-5084 or ASTM-D-4263 test and results submitted to a Concure Systems Representative.

PART 2- PRODUCTS

2.1 CONCRETE WATERPROOFING ADMIXTURE

- A. Manufacturer: Concure Systems 1618 E. Briarwood Terrace, Phoenix, AZ 85048
Contact: Emil Pikula Cell – (480) 820-7171, Fax (480) 820-7787, E-mail: epikula@cox.net
- B. Admixture: Concure Systems Admixture
- C. Accessory Materials.
 - 1. Concure Systems Crack Fill Binder.

2.2 MIXING

- A. Add 14 ounces of Concure admixture per 100 lbs. of cementitious material to ready mix truck at the batch plant, or jobsite before discharge, mix rapidly for 7 minutes. (Follow Manufacturer's Instructions).
- B. To be used in lieu of, designed, mix water. Not in addition to mix water. Do not alter water/cement ratio. w/c .45 or less and a maximum slump of 4 inches

- C. The addition of non-chlorinated admixtures is permitted. (Follow Manufacturer's Instructions).

2.3 TESTING

- A. Concure recommends either ASTM D-5084 or ASTM 4263 only.
- B. Concure Systems must be provided test results if ASTM-D-5084 is performed and a Concure Systems Representative or designated agent must be present for final inspection of ASTM-D-4263 test.

2.4 PRODUCT SUBSTITUTIONS

- A. Substitutions allowed meeting the following criteria:

Product must have MINIMUM 10 years no fail experience in the flooring/Concrete industry.

See sections 3300, 9600, 9900

PART 1- GENERAL

1.4 SUBMITTALS

- A. Closeout Submittals: Submit the following:
 - 1. Warranty: Warranty documents specified herein.

1.5 DELIVERY, STORAGE & HANDLING

- A. Store materials protected from exposure to harmful weather conditions and at a temperature above 45° Fahrenheit.

1.6 WARRANTY

- A. Project Warranty: Refer to Conditions of the Contract for Project warranty provisions.
- B. Manufacturer's Warranty: Submit, for the owner's acceptance, the manufacturer's standard warranty document executed by an authorized company official. The manufacturer's warranty is in addition to, and not a limitation of, other rights the Owner may have under provisions of the contract documents.
 - 1. Warranty Period: Ten years commencing on the date of acceptance of the project by the Owner or Notice of Completion whichever is earliest.
 - 2. Warranty Terms: Terms to include moisture related failures, including all finish floor materials and labor. Admixture warranty issued on completion of ASTM-D-5084 or ASTM-D-4263 test and results submitted to a Concure Systems Representative.

PART 2- PRODUCTS

2.1 CONCRETE WATERPROOFING ADMIXTURE

- A. Manufacturer: Concure Systems 1618 E. Briarwood Terrace, Phoenix, AZ 85048
Contact: Emil Pikula Cell – (480) 820-7171, Fax (480) 820-7787, E-mail: epikula@cox.net
- B. Admixture: Concure Systems Admixture
- C. Accessory Materials.
 - 1. Concure Systems Crack Fill Binder.

2.2 MIXING

- A. Add 14 ounces of Concure admixture per 100 lbs. of cementitious material to ready mix truck at the batch plant, or jobsite before discharge, mix rapidly for 7 minutes. (Follow Manufacturer's Instructions).
- B. To be used in lieu of, designed, mix water. Not in addition to mix water. Do not alter water/cement ratio. w/c .45 or less and a maximum slump of 4 inches.

- C. The addition of non-chlorinated admixtures is permitted. (Follow Manufacturer's Instructions).

2.3 TESTING

- A. Concure recommends either ASTM D-5084 or ASTM 4263 only.
- B. Concure Systems must be provided test results if ASTM-D-5084 is performed and a Concure Systems Representative or designated agent must be present for final inspection of ASTM-D-4263 test.

2.4 PRODUCT SUBSTITUTIONS

- A. Substitutions allowed meeting the following criteria:

Product must have MINIMUM 10 years no fail experience in the flooring/Concrete industry.

See sections, 3300, 7100, 9900

PART 1- GENERAL

1.1 SUBMITTALS

- A. Closeout Submittals: Submit the following:
 - 1. Warranty: Warranty documents specified herein.

1.2 DELIVERY, STORAGE & HANDLING

- A. Store materials protected from exposure to harmful weather conditions and at a temperature above 45° Fahrenheit.

1.3 WARRANTY

- A. Project Warranty: Refer to Conditions of the Contract for Project warranty provisions.
- B. Manufacturer's Warranty: Submit, for the owner's acceptance, the manufacturer's standard warranty document executed by an authorized company official. The manufacturer's warranty is in addition to, and not a limitation of, other rights the Owner may have under provisions of the contract documents.
 - 1. Warranty Period: Ten years commencing on the date of acceptance of the project by the Owner or Notice of Completion whichever is earliest.
 - 2. Warranty Terms: Terms to include moisture related failures, including all finish floor materials and labor. Admixture warranty issued on completion of ASTM-D-5084 or ASTM-D-4263 test and results submitted to a Concure Systems Representative.

PART 2- PRODUCTS

2.1 CONCRETE WATERPROOFING ADMIXTURE

- A. Manufacturer: Concure Systems 1618 E. Briarwood Terrace, Phoenix, AZ 85048
Contact: Emil Pikula Cell – (480) 820-7171, Fax (480) 820-7787, E-mail: epikula@cox.net
- B. Admixture: Concure Systems Admixture
- C. Accessory Materials.
 - 1. Concure Systems Crack Fill Binder.

2.2 MIXING

- A. Add 14 ounces of Concure admixture per 100 lbs. of cementitious material to ready mix truck at the batch plant, or jobsite before discharge, mix rapidly for 7 minutes. (Follow Manufacturer's Instructions).
- B. To be used in lieu of, designed, mix water. Not in addition to mix water. Do not alter water/cement ratio. w/c .45 or less and a maximum slump of 4 inches.

- C. The addition of non-chlorinated admixtures is permitted. (Follow Manufacturer's Instructions).

2.3 TESTING

- A. Concure recommends either ASTM D-5084 or ASTM 4263 only.
- B. Concure Systems must be provided test results if ASTM-D-5084 is performed and a Concure Systems representative or designated agent must be present for final inspection of ASTM-D-4263 test.

2.4 PRODUCT SUBSTITUTIONS

- A. Substitutions allowed meeting the following criteria:

Product must have MINIMUM 10 years no fail experience in the flooring/Concrete industry.

See sections 3300, 7100, 9600